Resene Paints (Australia) Limited

Version No: 2.3 Safety Data Sheet according to WHS and ADG requirements Chemwatch Hazard Alert Code: 4

Issue Date: 25/02/2020 Print Date: 26/02/2020 S.GHS.AUS.EN

SECTION 1 IDENTIFICATION OF THE SUBSTANCE / MIXTURE AND OF THE COMPANY / UNDERTAKING

Product Identifier

Product name	Altex Thinning Solvent #127	
Synonyms	Not Available	
Proper shipping name	PAINT (including paint, lacquer, enamel, stain, shellac, varnish, polish, liquid filler and liquid lacquer base) or PAINT RELATED MATERIAL (including paint thinning or reducing compound)	
Other means of identification	Not Available	
Relevant identified uses of the substance or mixture and uses advised against		
Relevant identified uses	Thinning Solvent	

Details of the supplier of the safety data sheet

Registered company name	Resene Paints (Australia) Limited	
Address	64 Link Drive Queensland 4207 Australia	
Telephone	+61 7 55126600	
Fax	+61 7 55126697	
Website	www.resene.com.au	
Email	Not Available	

Emergency telephone number

Association / Organisation	AUSTRALIAN POISONS CENTRE	CHEMWATCH EMERGENCY RESPONSE
Emergency telephone numbers	131126	+61 1800 951 288
Other emergency telephone numbers	Not Available	+61 2 9186 1132

Once connected and if the message is not in your prefered language then please dial 01

SECTION 2 HAZARDS IDENTIFICATION

Classification of the substance or mixture

HAZARDOUS CHEMICAL. DANGEROUS GOODS. According to the WHS Regulations and the ADG Code.

Poisons Schedule	Not Applicable	
Classification ^[1]	Eye Irritation Category 2A, Specific target organ toxicity - single exposure Category 3 (narcotic effects), Specific target organ toxicity - repeated exposure Category 2, Flammable Liquid Category 2, Specific target organ toxicity - single exposure Category 3 (respiratory tract irritation), Acute Toxicity (Oral) Category 4, Skin Corrosion/Irritation Category 2, Reproductive Toxicity Category 2, Aspiration Hazard Category 1, Carcinogenicity Category 2, Chronic Aquatic Hazard Category 3	
Legend:	1. Classified by Chemwatch; 2. Classification drawn from HCIS; 3. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI	
Label elements		
	$\land \land \land$	

SIGNAL WORD D

DANGER

Hazard pictogram(s)

Hazard statement(s)		
H319	Causes serious eye irritation.	
H336	May cause drowsiness or dizziness.	
H373	May cause damage to organs through prolonged or repeated exposure. (Not specified) (Oral, Dermal, Inhalation)	
H225	Highly flammable liquid and vapour.	
H335	May cause respiratory irritation.	
H302	Harmful if swallowed.	
H315	Causes skin irritation.	

H361	Suspected of damaging fertility or the unborn child.	
H304	May be fatal if swallowed and enters airways.	
H351	Suspected of causing cancer.	
H412	Harmful to aquatic life with long lasting effects.	

Supplementary statement(s)

Not Applicable

Precautionary statement(s) Prevention

P201	Obtain special instructions before use.	
P210	Keep away from heat/sparks/open flames/hot surfaces No smoking.	
P260	Do not breathe mist/vapours/spray.	
P271	Use in a well-ventilated area.	
P281	Use personal protective equipment as required.	
P240	Ground/bond container and receiving equipment.	
P241	Use explosion-proof electrical/ventilating/lighting/intrinsically safe equipment.	
P242	Use only non-sparking tools.	
P243	Take precautionary measures against static discharge.	
P270	Do not eat, drink or smoke when using this product.	
P273	Avoid release to the environment.	
P280	Wear protective gloves/protective clothing/eye protection/face protection.	

Precautionary statement(s) Response

P301+P310	IF SWALLOWED: Immediately call a POISON CENTER or doctor/physician.	
P308+P313	IF exposed or concerned: Get medical advice/attention.	
P321	Specific treatment (see advice on this label).	
P331	Do NOT induce vomiting.	
P362	Take off contaminated clothing and wash before reuse.	
P370+P378	In case of fire: Use alcohol resistant foam or normal protein foam for extinction.	
P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P337+P313	If eye irritation persists: Get medical advice/attention.	
P301+P312	IF SWALLOWED: Call a POISON CENTER or doctor/physician if you feel unwell.	
P302+P352	IF ON SKIN: Wash with plenty of water and soap.	
P303+P361+P353	IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower.	
P304+P340	IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.	
P330	Rinse mouth.	
P332+P313	If skin irritation occurs: Get medical advice/attention.	

Precautionary statement(s) Storage

F403+F235 51016	ore in a well-ventilated place. Keep cool.
P405 Store	pre locked up.

Precautionary statement(s) Disposal

P501 Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

SECTION 3 COMPOSITION / INFORMATION ON INGREDIENTS

Substances

See section below for composition of Mixtures

Mixtures

CAS No	%[weight]	Name
Not Available	20-30	xylene
Not Available	10-20	propylene glycol monomethyl ether acetate
64742-95-6	10-20	naphtha petroleum, light aromatic solvent
78-93-3	40-50	methyl ethyl ketone

SECTION 4 FIRST AID MEASURES

Description of first aid measures

Eye Contact

- If this product comes in contact with the eyes: • Wash out immediately with fresh running water.
 - _____

	 Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	 If skin or hair contact occurs: Immediately flush body and clothes with large amounts of water, using safety shower if available. Quickly remove all contaminated clothing, including footwear. Wash skin and hair with running water. Continue flushing with water until advised to stop by the Poisons Information Centre. Transport to hospital, or doctor.
Inhalation	 If fumes or combustion products are inhaled remove from contaminated area. Lay patient down. Keep warm and rested. Prostheses such as false teeth, which may block airway, should be removed, where possible, prior to initiating first aid procedures. Apply artificial respiration if not breathing, preferably with a demand valve resuscitator, bag-valve mask device, or pocket mask as trained. Perform CPR if necessary. Transport to hospital, or doctor, without delay.
Ingestion	 If spontaneous vomiting appears imminent or occurs, hold patient's head down, lower than their hips to help avoid possible aspiration of vomitus. If swallowed do NOT induce vomiting. If vomiting occurs, lean patient forward or place on left side (head-down position, if possible) to maintain open airway and prevent aspiration. Observe the patient carefully. Never give liquid to a person showing signs of being sleepy or with reduced awareness; i.e. becoming unconscious. Give water to rinse out mouth, then provide liquid slowly and as much as casualty can comfortably drink. Seek medical advice. Avoid giving milk or oils. Avoid giving alcohol.

Indication of any immediate medical attention and special treatment needed

Any material aspirated during vomiting may produce lung injury. Therefore emesis should not be induced mechanically or pharmacologically. Mechanical means should be used if it is considered necessary to evacuate the stomach contents; these include gastric lavage after endotracheal intubation. If spontaneous vomiting has occurred after ingestion, the patient should be monitored for difficult breathing, as adverse effects of aspiration into the lungs may be delayed up to 48 hours. for simple ketones:

BASIC TREATMENT

- Establish a patent airway with suction where necessary.
- Watch for signs of respiratory insufficiency and assist ventilation as necessary.
- Administer oxygen by non-rebreather mask at 10 to 15 l/min.
- Monitor and treat, where necessary, for pulmonary oedema.
- Monitor and treat, where necessary, for shock.
- DO NOT use emetics. Where ingestion is suspected rinse mouth and give up to 200 ml water (5mL/kg recommended) for dilution where patient is able to swallow, has a strong gag reflex and does not drool.
- Give activated charcoal.

ADVANCED TREATMENT

- Consider orotracheal or nasotracheal intubation for airway control in unconscious patient or where respiratory arrest has occurred.
- Consider intubation at first sign of upper airway obstruction resulting from oedema.
- Positive-pressure ventilation using a bag-valve mask might be of use.
- Monitor and treat, where necessary, for arrhythmias.
- Start an IV D5W TKO. If signs of hypovolaemia are present use lactated Ringers solution. Fluid overload might create complications.
- Drug therapy should be considered for pulmonary oedema.
- Hypotension with signs of hypovolaemia requires the cautious administration of fluids. Fluid overload might create complications.
- Treat seizures with diazepam.
- Proparacaine hydrochloride should be used to assist eye irrigation.

EMERGENCY DEPARTMENT

- Laboratory analysis of complete blood count, serum electrolytes, BUN, creatinine, glucose, urinalysis, baseline for serum aminotransferases (ALT and AST), calcium, phosphorus and magnesium, may assist in establishing a treatment regime. Other useful analyses include anion and osmolar gaps, arterial blood gases (ABGs), chest radiographs and electrocardiograph.
- Positive end-expiratory pressure (PEEP)-assisted ventilation may be required for acute parenchymal injury or adult respiratory distress syndrome.
- Consult a toxicologist as necessary.

BRONSTEIN, A.C. and CURRANCE, P.L.

EMERGENCY CARE FOR HAZARDOUS MATERIALS EXPOSURE: 2nd Ed. 1994

for naphthalene intoxication: Naphthalene requires hepatic and microsomal activation prior to the production of toxic effects. Liver microsomes catalyse the initial synthesis of the reactive 1,2-epoxide intermediate which is subsequently oxidised to naphthalene dihydrodiol and alpha-naphthol. The 2-naphthoquinones are thought to produce haemolysis, the 1,2-naphthoquinones are thought to be responsible for producing cataracts in rabbits, and the glutathione-adducts of naphthalene-1,2-oxide are probably responsible for pulmonary toxicity. Suggested treatment reqime:

- Induce emesis and/or perform gastric lavage with large amounts of warm water where oral poisoning is suspected.
- Instill a saline cathartic such as magnesium or sodium sulfate in water (15 to 30g).
- Demulcents such as milk, egg white, gelatin, or other protein solutions may be useful after the stomach is emptied but oils should be avoided because they promote absorption.
- If eyes/skin contaminated, flush with warm water followed by the application of a bland ointment.
- Severe anaemia, due to haemolysis, may require small repeated blood transfusions, preferably with red cells from a non-sensitive individual.
- Where intravascular haemolysis, with haemoglobinuria occurs, protect the kidneys by promoting a brisk flow of dilute urine with, for example, an osmotic diuretic such as mannitol. It may be useful to alkalinise the urine with small amounts of sodium bicarbonate but many researchers doubt whether this prevents blockage of the renal tubules.
- Use supportive measures in the case of acute renal failure. GOSSELIN, SMITH HODGE: Clinical Toxicology of Commercial Products, 5th Ed.
- For acute or short term repeated exposures to petroleum distillates or related hydrocarbons:
- Primary threat to life, from pure petroleum distillate ingestion and/or inhalation, is respiratory failure.
- Patients should be quickly evaluated for signs of respiratory distress (e.g. cyanosis, tachypnoea, intercostal retraction, obtundation) and given oxygen. Patients with inadequate tidal volumes or poor arterial blood gases (pO2 50 mm Hg) should be intubated.
- Arrhythmias complicate some hydrocarbon ingestion and/or inhalation and electrocardiographic evidence of myocardial injury has been reported; intravenous lines and cardiac monitors should be established in obviously symptomatic patients. The lungs excrete inhaled solvents, so that hyperventilation improves clearance.
- A chest x-ray should be taken immediately after stabilisation of breathing and circulation to document aspiration and detect the presence of pneumothorax.
- Epinephrine (adrenalin) is not recommended for treatment of bronchospasm because of potential myocardial sensitisation to catecholamines. Inhaled cardioselective
- bronchodilators (e.g. Alupent, Salbutamol) are the preferred agents, with aminophylline a second choice.
- ► Lavage is indicated in patients who require decontamination; ensure use of cuffed endotracheal tube in adult patients. [Ellenhorn and Barceloux: Medical Toxicology]

SECTION 5 FIREFIGHTING MEASURES

Extinguishing media

- Alcohol stable foam.
- Dry chemical powder.
- BCF (where regulations permit).
- Carbon dioxide.
- Water spray or fog Large fires only.

Special hazards arising from the substrate or mixture

Fire Incompatibility	y Avoid contamination with oxidising agents i.e. nitrates, oxidising acids, chlorine bleaches, pool chlorine etc. as ignition may result		
Advice for firefighters			
Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. May be violently or explosively reactive. Wear breathing apparatus plus protective gloves in the event of a fire. Prevent, by any means available, spillage from entering drains or water course. Consider evacuation (or protect in place). Fight fire from a safe distance, with adequate cover. If safe, switch off electrical equipment until vapour fire hazard removed. Use water delivered as a fine spray to control the fire and cool adjacent area. Avoid spraying water onto liquid pools. Do not approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. 		
	Continued		

	If safe to do so, remove containers from path of fire.
Fire/Explosion Hazard	 Liquid and vapour are highly flammable. Severe fire hazard when exposed to heat, flame and/or oxidisers. Vapour may travel a considerable distance to source of ignition. Heating may cause expansion or decomposition leading to violent rupture of containers. On combustion, may emit toxic fumes of carbon monoxide (CO). Combustion products include: , , carbon dioxide (CO2) , , other pyrolysis products typical of burning organic material. Contains low boiling substance: Closed containers may rupture due to pressure buildup under fire conditions.
HAZCHEM	•3YE
Internet	

SECTION 6 ACCIDENTAL RELEASE MEASURES

Personal precautions, protective equipment and emergency procedures

See section 8

Environmental precautions

See section 12

Methods and material for containment and cleaning up

Minor Spills	 Remove all ignition sources. Clean up all spills immediately. Avoid breathing vapours and contact with skin and eyes. Control personal contact with the substance, by using protective equipment. Contain and absorb small quantities with vermiculite or other absorbent material. Wipe up. Collect residues in a flammable waste container.
Major Spills	 Clear area of personnel and move upwind. Alert Fire Brigade and tell them location and nature of hazard. May be violently or explosively reactive. Wear breathing apparatus plus protective gloves. Prevent, by any means available, spillage from entering drains or water course. Consider evacuation (or protect in place). No smoking, naked lights or ignition sources. Increase ventilation. Stop leak if safe to do so. Water spray or fog may be used to disperse /absorb vapour. Contain spill with sand, earth or vermiculite. Use only spark-free shovels and explosion proof equipment. Collect recoverable product into labelled containers for recycling. Absorb remaining product with sand, earth or vermiculite. Collect solid residues and seal in labelled drums for disposal. Wash area and prevent runoff into drains. If contamination of drains or waterways occurs, advise emergency services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 HANDLING AND STORAGE

Precautions for safe handling

 Safe handling Safe handling When solves the substance may concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with DETONATION potential. No DOT Concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with DETONATION potential. No DOT Concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with DETONATION potential. No NoT concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with excess 5% aqueous ferrous sulfate solution or by percolation through excess to decive datumina. Do NOT concentrate by evaporation, or evaporate extracts to dryness, as residues or is distillate or percovides with excess 5% aqueous ferrous sulfate solution or by percolation through be decived by treatment with polar solvents which have been dry by percolation through counting and busing with excess 5% aqueous ferrous sulfate solution or by percolation through be decived by the dryne solvents solved by percolation from explosive peroxides by percolation from explosive peroxides by percolation through counters or distilled or otherwise treated to concentrate the percented with both the extracts to dryness, as residues and contain explosive peroxides with DETONATION potential. Any static discharge is also a source of hazard. Before any distillation process remove trace peroxides by shaking with excess 5% aqueous ferrous sulfate solution or by percolation through aclumina. Distillation results in uninhibited ether distillate with considerably increased hazard because of risk of peroxide formation on storage. Add inhibitor to any distillate as required. When solvents have been freed from peroxides by percolation through columns of activated alumina, the absorbed peroxides with percenters which have been enperoxides which may become h		
	Safe handling	The conductivity of this material may make it a static accumulator., A liquid is typically considered nonconductive if its conductivity is below 100 pS/m and is considered semi-conductive if its conductivity is below 10 000 pS/m. Whether a liquid is nonconductive or semi-conductive, the precautions are the same., A number of factors, for example liquid temperature, presence of contaminants, and anti-static additives can greatly influence the conductivity of a liquid. Even with proper grounding and bonding, this material can still accumulate an electrostatic charge. If sufficient charge is allowed to accumulate, electrostatic discharge and ignition of flammable air-vapour mixtures can occur. • Containers, even those that have been emptied, may contain explosive vapours. • Do NOT cut, drill, grind, weld or perform similar operations on or near containers. Containe so whose that have been emptied, may contain explosive vapours. • Do NOT cut, drill, grind, weld or perform similar operations on or near containers. Containes low boiling substance: Storage in sealed containers may result in pressure buildup causing violent rupture of containers not rated appropriately. • Check for buiging containers. • Vent periodically • Always release caps or seals slowly to ensure slow dissipation of vapours The tendency of many ethers to form explosive peroxides is well documented. Ethers lacking non-methyl hydrogen atoms adjacent to the ether link are thought to be relatively safe • DO NOT concentrate by evaporation, or evaporate extracts to dryness, as residues may contain explosive peroxides with DETONATION potential. • And inhibitor to any distillate as required. • Distillation results in uninhibited ether distillate with considerably increased hazard because of risk of peroxide formation on storage. • Add inhibitor to any distillate as required.

	chemicals are subject to peroxidation. An expiration date should be determined. The chemical should either be treated to remove peroxides
	or disposed of before this date.
	I ne person or laboratory receiving the chemical should record a receipt date on the bottle. The individual opening the container should add an opening date
	 Unopened containers received from the supplier should be safe to store for 18 months.
	Opened containers should not be stored for more than 12 months.
	 Electrostatic discharge may be generated during pumping - this may result in fire. Ensure electrical continuity by bonding and grounding (earthing) all equipment
	 Restrict line velocity during pumping in order to avoid generation of electrostatic discharge (<=1 m/sec until fill pipe submerged to twice its
	diameter, then <= 7 m/sec).
	 Avoid splash filling. De NOT use compressed air far filling discharging or handling operations.
	 Do NOT use compressed air for filling discharging or handling operations. Avoid all personal contact, including inhalation.
	 Wear protective clothing when risk of exposure occurs.
	Use in a well-ventilated area.
	 Prevent concentration in hollows and sumps. DO NOT enter confined spaces until atmosphere has been checked
	 Avoid smoking, naked lights, heat or ignition sources.
	When handling, DO NOT eat, drink or smoke.
	 Vapour may ignite on pumping or pouring due to static electricity. POOT use there have been been been been been been been be
	Forward use plastic buckets. Farth and secure metal containers when dispensing or pouring product
	 Use spark-free tools when handling.
	Avoid contact with incompatible materials.
	Keep containers securely sealed.
	 Avoid physical damage to containers. Always wash bands with soan and water after bandling
	Work clothes should be laundered separately.
	► Use good occupational work practice.
	 Observe manufacturer's storage and handling recommendations contained within this SDS.
	Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions. DO NOT allow clothing wet with material to stay in contact with skin.
	Store is printed centainers in approved flame proof area
	 No smoking, naked lights, heat or ignition sources.
	DO NOT store in pits, depressions, basements or areas where vapours may be trapped.
Other information	► Keep containers securely sealed.
	 Store away from incompatible materials in a cool, dry well ventilated area. Deside control consistent provided the provided of the logical control of the log
	 Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS.
Conditions for safe storage, in	cluding any incompatibilities
	Packing as supplied by manufacturer.
	 Plastic containers may only be used if approved for flammable liquid. Cheat that containers may only the used lad and free from local to the second sec
	• Check that containers are clearly labelled and free from leaks.
	For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner
	For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure.
	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C)
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging:
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used.
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product thar requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product tharing a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product thaving a viscosity of at least 250 cSt. (23 deg. C) Manufactured product thaving a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may denerate electrostatic charges, due to low conductivity, on flow or agitation
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product thar equires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes:
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attacks some plastics, rubber and coatings may ignite or explode in contact with strong oxidisers, can result from the contact between aromatic rings and strong oxidising agents.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For maturfactured product hat requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer package is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attacks some plastics, rubber and coatings may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents.
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group 1 there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation xylenes: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics can react exothermically with bases and with dia
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may ignite or explode in contact with strong oxidisers, 0, can result from the contact between aromatic rings and strong oxidising agents. Aromatics can react exothermically with bases and with diazo compounds. For alkyl aromatics: The alkyl side chain of aromatic rings can undergo oxidation by several mechanisms. The most common and dominant one is the attack by wrindini
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics can react exothermically with bases and with diazo compounds. For alkyl aromatics: The alkyl side chain of aromatic rings can undergo oxidation by several mechanisms. The most common and dominant one is the a
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For maturials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable perxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics can react exothermically with bases and with diazo compounds. For alkyl aromatics: The alkyl side chain of aromatic rings can undergo oxidation by several mechanisms. The most common and dominant one is the attack by oxidation product formed (provided a hydroge
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 260 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group 1 there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges on glow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics: readt subter and coatings may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to expl
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 260 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and catridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group 1 there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable percoides in storage, or on contact with propanol or hydrogen peroxide attack some plastics, rubber and coatings may gipite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may gipite or explode in contact with strong oxidisers, can result from the contact between aromatic rings and strong oxidising agents. Aromatics: The akkyl side chain of aromatic rings can undergo oxidation by several mechanisms. The most common and do
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 268 cSt. (23 deg. C) For manufactured product that requires stiring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethore: reacts violentiy with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics can react exothermically with bases and with diazo compounds. For alkyl aromatics: The alkyl side chain of aromatic rings can undergo oxidation by several mechanisms. The most common and dominant one is the attack by oxidation at benzylic carbon
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 280 of Ct. (23 deg. C) For manufactured product having a viscosity of at least 250 of Ct. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 of Ct. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 of Ct. (2) deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and carridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with iner and outer packages are used, and the inner packages are of glass, there must be sufficient inert absorbent to absorb any spillage, unless the outer packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attack some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Mylenes: may generate electrostatic charges on flow or agitation due to low conductivity. Migor
Suitable container	 For low viscosity materials (i) : Drums and jerry cans must be of the non-removable head type. (ii) : Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 268 of CS1 (23 deg, C) For manufactured product having a viscosity of at least 250 of CS1. (23 deg, C) Manufactured product that requires stirring before use and having a viscosity of at least 20 of CS1 (25 deg, C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and carridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages are used, and the inner packages are of glass, there must be sufficient inert absorbent to absorb any spillage, unless the outer packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attack some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes: may ginite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may generate electrostatic charges on flow or agitation due t
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For marufactured product having a viscosity of at least 2680 CSt. (23 deg. C) For manufactured product having a viscosity of at least 260 CSt. (23 deg. C) Manufactured product having a viscosity of at least 260 CSt. (23 deg. C) Manufactured product having a viscosity of at least 260 CSt. (23 deg. C) Manufactured product have that requires string before use and having a viscosity of at least 20 CSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartidges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum s incompatible with inorganic acids, aliphatic amines, armonia, caustics, iscorpanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may ignite or explode in contact with bases and with diazo compounds.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For manufactured product having a viscosity of at least 250 cSt. (23 deg. C) Manufactured product that requires stirring before use and having a viscosity of at least 20 cSt (25 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages are used, and the inner packages are of glass, there must be sufficient inert absorbent to absorb any spillage, unless the outer packagings are glass and contain liquids of packing group 1 there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with inorganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable perxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation Xylenes:: may ignite or explode in contact with strong oxidisers, 1,3-dichloro-5,5-dimethylhydantoin, uranium fluoride attack some plastics, rubber and coatings may generate electrostatic charges on flow or agitation due to low conductivity.
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 260 cSt. (23 deg. C) For materials with a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 250 cSt. (23 deg. C). Manufactured product having a viscosity of at least 250 cSt. (23 deg. C): (i) Removable head packaging; (ii) Cans with friction closures and (iii) low pressure tubes and cartridges may be used. Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, eleum is incompatible with horganic acids, aliphatic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic adi forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics. may generate electrostatic charges, due to low conductivity, on flow or agitation type reaction, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics are neat exothermically with bases and with diazo compounds. For alkyl atomatics: For alkyl atomatics: For alkyl atomatics: Foralkyl atomatics: For alkyl atomatics:
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 260 cSt. (23 deg. C) For materials with a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 250 cSt. (23 deg. C). Manufactured product having a viscosity of at least 250 cSt. (23 deg. C). Manufactured product having a viscosity of at least 250 cSt. (23 deg. C). Where combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages. In addition, where inner packagings are glass and contain liquids of packing group 1 there must be sufficient inert absorbent to absorb any spillage, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic. Methyl ethyl ketone: reacts violently with strong oxidisers, aldehydes, nitric acid, perchloric acid, potassium tert-butoxide, oleum is incompatible with hiorganic acids, aliphalic amines, ammonia, caustics, isocyanates, pyridines, chlorosulfonic aid forms unstable peroxides in storage, or on contact with propanol or hydrogen peroxide attack some plastics. may generate electrostatic charges on flow or agitation due to low conductivity. Vigorous reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. Aromatics: The alkyl side chain of aromatic rings can undergo oxidiation by several mechanisms. The most common and dominant one is the atttack by oxidation at benzylic carbod as subtisfued by oxygen<!--</th-->
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 260 cSt. (23 deg. C) For materials with a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 280 cSt. (23 deg. C) Manufactured product having a viscosity of at least 280 cSt. (23 deg. C) Manufactured product having a viscosity of at least 280 cSt. (23 deg. C) Manufactured product having a viscosity of at least 280 cSt. (23 deg. C): Mare combination packages are used, and the inner packages are of glass, there must be sufficient inert cushioning material in contact with inner and outer packages In addition, where inner packagings are glass and contain liquids of packing group I there must be sufficient inert absorbent to absorb any spillage, unless the outer packages and annonia, caustics, iscovanates, pyridines, chlorosuffori ald forms unstable proxides in storage, or on contact with propanol or hydrogen peroxide attacks some plastics may generate electrostatic charges, due to low conductivity, on flow or agitation tracks come plastics, rubber and coatings may generate electrostatic charges on low or agitation due to low conductivity. Vigrours reactions, sometimes amounting to explosions, can result from the contact between aromatic rings and strong oxidising agents. A romatics can react exothermically with bases and with diazo compounds. For alkyl aide chain of aromatic rings can undergo oxidation by several mechanisms. The most common and dominant one is the attack by oxidation at be intermediate formed is stabilised by resonance structure of the ring. For alkyl side chain of aromatic rings can undergo oxidation
Suitable container	 For low viscosity materials (i): Drums and jerry cans must be of the non-removable head type. (ii): Where a can is to be used as an inner package, the can must have a screwed enclosure. For materials with a viscosity of at least 2680 cSt. (23 deg. C) For materials with a viscosity of at least 2680 cSt. (23 deg. C) Manufactured product having a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 260 cSt. (23 deg. C) Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Manufactured product having a viscosity of at least 260 cSt. (23 deg. C): Matter at least 260 cSt. (24 deg. C): Manufactured product having a viscosity of at least 260 cSt. (24

- flash-point large containers may first need to be purged and inerted with nitrogen prior to loading
- In the presence of strong bases or the salts of strong bases, at elevated temperatures, the potential exists for runaway reactions.
- Contact with aluminium should be avoided; release of hydrogen gas may result- glycol ethers will corrode scratched aluminium surfaces.
 May discolour in mild steel/ copper; lined containers, glass or stainless steel is preferred
 - B Glycols and their ethers undergo violent decomposition in contact with 70% perchloric acid. This seems likely to involve formation of the glycol perchlorate esters (after scission of ethers) which are explosive, those of ethylene glycol and 3-chloro-1,2-propanediol being more powerful than glyceryl nitrate, and the former so sensitive that it explodes on addition of water . Investigation of the hazards associated with use of 2-butoxyethanol for alloy electropolishing showed that mixtures with 50-95% of acid at 20 deg C, or 40-90% at 75 C, were explosive and initiable by sparks. Sparking caused mixtures with 40-50% of acid to become explosive, but 30% solutions appeared safe under static conditions of temperature and concentration.

Ketones in this group:

- ▶ are reactive with many acids and bases liberating heat and flammable gases (e.g., H2).
- ▶ react with reducing agents such as hydrides, alkali metals, and nitrides to produce flammable gas (H2) and heat.
- ▶ are incompatible with isocyanates, aldehydes, cyanides, peroxides, and anhydrides
- react violently with aldehydes, HNO3 (nitric acid), HNO3 + H2O2 (mixture of nitric acid and hydrogen peroxide), and HCIO4 (perchloric acid).
 may react with hydrogen peroxide to form unstable peroxides; many are heat- and shock-sensitive explosives.

A significant property of most ketones is that the hydrogen atoms on the carbon next to the carbonyl group are relatively acidic when compared to hydrogen atoms in typical hydrocarbons. Under strongly basic conditions these hydrogen atoms may be abstracted to form an enolate anion. This property allows ketones, especially methyl ketones, to participate in condensation reactions with other ketones and aldehydes. This type of condensation reaction is favoured by high substrate concentrations and high pH (greater than 1 wt% NaOH).

- Propylene glycol monomethyl ether acetate:
 - may polymerise unless properly inhibited due to peroxide formation
 - ▶ should be isolated from UV light, high temperatures, free radical initiators
 - may react with strong oxidisers to produce fire and/ or explosion
- ▶ reacts violently with with sodium peroxide, uranium fluoride
- ▶ is incompatible with sulfuric acid, nitric acid, caustics, aliphatic amines, isocyanates, boranes



X — Must not be stored together

- 0 May be stored together with specific preventions
- May be stored together

SECTION 8 EXPOSURE CONTROLS / PERSONAL PROTECTION

3,000 ppm

Control parameters

OCCUPATIONAL EXPOSURE LIMITS (OEL)

INGREDIENT DATA

Source	Ingredient	Material name	TWA		STEL		Peak		Notes
Australia Exposure Standards	methyl ethyl ketone	Methyl ethyl ketone (MEK)	150 ppm / 4	45 mg/m3	890 mg/r	m3 / 300 ppm	Not Avai	ilable	Not Available
EMERGENCY LIMITS									
Ingredient	Material name			TEEL-1		TEEL-2		TEEL	-3
methyl ethyl ketone	Butanone, 2-; (Methyl e	ethyl ketone; MEK)		Not Available		Not Available		Not Av	vailable
Ingredient	Original IDLH			Revised	d IDLH				
naphtha petroleum, light aromatic solvent	Not Available			Not Ava	ilable				

OCCUPATIONAL EXPOSURE BANDING

Ingredient	Occupational Exposure Band Rating	Occupational Exposure Band Limit	
naphtha petroleum, light aromatic solvent	E	≤ 0.1 ppm	
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposure band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.		

Not Available

Exposure controls

methyl ethyl ketone

Appropriate engineering controls	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation to "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure. For flammable liquids and flammable gases, local exhaust ventilation or a process enclosure ventilation system may be required equipment should be explosion-resistant. Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture velocities circulating air required to effectively remove the contaminant. Type of Contaminant:	ring controls can ction. hat strategically design of a I. Ventilation s" of fresh
	Type of Contaminant:	Air Speed:

	solvent, vapours, degreasing etc., evaporating from tank (in	0.25-0.5 m/s (50-100 f/min.)			
	aerosols, fumes from pouring operations, intermittent conta plating acid fumes, pickling (released at low velocity into zo	ner filling, low speed conveyer transfers, welding, spray drift, ne of active generation)	0.5-1 m/s (100-200 f/min.)		
	direct spray, spray painting in shallow booths, drum filling, c generation into zone of rapid air motion)	onveyer loading, crusher dusts, gas discharge (active	1-2.5 m/s (200-500 f/min.)		
	Within each range the appropriate value depends on:				
	Lower end of the range	Upper end of the range			
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents			
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion	4: Small hood-local control only			
	Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 1-2 m/s (200-400 f/min.) for extraction of solvents generated in a tank 2 meters distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction paparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.				
Personal protection					
Eye and face protection	 Safety glasses with side shields. Chemical goggles. Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or pational equivalent] 				
Skin protection	See Hand protection below				
Hands/feet protection	 Wear chemical protective gloves, e.g. PVC. Wear safety footwear or safety gumboots, e.g. Rubber The selection of suitable gloves does not only depend on the manufacturer. Where the chemical is a preparation of several and has therefore to be checked prior to the application. The exact break through time for substances has to be obtain making a final choice. Personal hygiene is a key element of effective hand care. Glo washed and dried thoroughly. Application of a non-perfumed i Suitability and durability of glove type is dependent on usage. frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe EN 3 When prolonged or frequently repeated conta greater than 240 minutes according to EN 374, AS/ When only brief contact is expected, a glove according to EN 374, AS/NZS 2161.10.1 or nationa Some glove polymer types are less affected I long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are r Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically great It should be emphasised that glove thickness is not necessari efficiency of the glove will be dependent on the exact compos consideration of the task requirements and knowledge of bread gloves are only likely to give short duration protection. Thinner gloves (down to 0.1 mm or less) may gloves are only likely to give short duration protection. Thicker gloves (up to 3 mm or more) may be abrasion or puncture potential Gloves mus	material, but also on further marks of quality which vary from man substances, the resistance of the glove material can not be calcul ed from the manufacturer of the protective gloves and has to be o ves must only be worn on clean hands. After using gloves, hands noisturiser is recommended. Important factors in the selection of gloves include: 74, US F739, AS/NZS 2161.1 or national equivalent). Inter may occur, a glove with a protection class of 5 or higher (break NZS 2161.10.1 or national equivalent) is recommended. with a protection class of 3 or higher (breakthrough time greater th l equivalent) is recommended. by movement and this should be taken into account when conside ated as: ater than 0.35 mm, are recommended. y a good predictor of glove resistance to a specific chemical, as th ition of the glove material. Therefore, glove selection should also I kthrough times. acturer, the glove type and the glove model. Therefore, the manuf selection of the most appropriate glove for the task. rying thickness may be required for specific tasks. For example: be required where a high degree of manual dexterity is needed. I on and would normally be just for single use applications, then disp required where there is a mechanical (as well as a chemical) risk hands should be washed and dried thoroughly. Application of a m	ufacturer to lated in advance bserved when should be through time han 60 minutes ring gloves for he permeation be based on facturers' However, these posed of. i.e. where there is ion-perfumed		

Body protection See Other protection below

▶ Overalls.
▶ PVC Apron.
PVC protective suit may be required if exposure severe.
▶ Eyewash unit.
Ensure there is ready access to a safety shower.
Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.
For large scale or continuous use wear tight-weave non-static clothing (no metallic fasteners, cuffs or pockets).
Non sparking safety or conductive footwear should be considered. Conductive footwear describes a boot or shoe with a sole made from a conductive compound chemically bound to the bottom components, for permanent control to electrically ground the foot an shall dissipate static electricity from the body to reduce the possibility of ignition of volatile compounds. Electrical resistance must range between 0 to 500,000 ohms. Conductive shoes should be stored in lockers close to the room in which they are worn. Personnel who have been issued conductive footwear should not wear them from their place of work to their homes and return.

Recommended material(s)

GLOVE SELECTION INDEX

Glove selection is based on a modified presentation of the:

"Forsberg Clothing Performance Index".

The effect(s) of the following substance(s) are taken into account in the *computer-generated* selection:

Altex Thinning Solvent #127

Material	CPI
BUTYL	C
BUTYL/NEOPRENE	С
HYPALON	C
NATURAL RUBBER	С
NATURAL+NEOPRENE	C
NEOPRENE	С
NEOPRENE/NATURAL	C
NITRILE	С
NITRILE+PVC	С
PE/EVAL/PE	C
PVA	С
PVC	С
SARANEX-23	С
TEFLON	С
VITON	С
VITON/NEOPRENE	С

* CPI - Chemwatch Performance Index

A: Best Selection

B: Satisfactory; may degrade after 4 hours continuous immersion

C: Poor to Dangerous Choice for other than short term immersion

NOTE: As a series of factors will influence the actual performance of the glove, a final selection must be based on detailed observation. -

* Where the glove is to be used on a short term, casual or infrequent basis, factors such as "feel" or convenience (e.g. disposability), may dictate a choice of gloves which might otherwise be unsuitable following long-term or frequent use. A qualified practitioner should be consulted.

SECTION 9 PHYSICAL AND CHEMICAL PROPERTIES

Information on basic physical and chemical properties

 In the computer computer

 exceeds the "Exposure Standard" (or ES), respiratory protection is required. Degree of protection varies with both face-piece and Class of filter; the nature of protection varies with Type of filter.

 CPI
 Required Minimum Protection Factor
 Half-Face Respirator
 Full-Face Respirator
 Powered Air Respirator

Respiratory protection

ANSI Z88 or national equivalent)

Protection Factor	Respirator	Respirator	Respirator
up to 5 x ES	A-AUS / Class 1	-	A-PAPR-AUS / Class 1
up to 25 x ES	Air-line*	A-2	A-PAPR-2
up to 50 x ES	-	A-3	-
50+ x ES	-	Air-line**	-

Type A Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001,

Where the concentration of gas/particulates in the breathing zone, approaches or

* - Continuous-flow; ** - Continuous-flow or positive pressure demand ^ - Full-face

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

- Cartridge respirators should never be used for emergency ingress or in areas of unknown vapour concentrations or oxygen content.
- The wearer must be warned to leave the contaminated area immediately on detecting any odours through the respirator. The odour may indicate that the mask is not functioning properly, that the vapour concentration is too high, or that the mask is not properly fitted. Because of these limitations, only restricted use of cartridge respirators is considered appropriate.
- Cartridge performance is affected by humidity. Cartridges should be changed after 2 hr of continuous use unless it is determined that the humidity is less than 75%, in which case, cartridges can be used for 4 hr. Used cartridges should be discarded daily, regardless of the length of time used

normation on basic physical and chemical properties				
Appearance	Clear liquid			
Physical state	Liquid	Relative density (Water - 1)	0.845	
r nysicai state		Relative density (water = 1)	0.043	
Odour	Not Available	Partition coefficient n-octanol / water	Not Available	
Odour threshold	Not Available	Auto-ignition temperature (°C)	463	
pH (as supplied)	Not Available	Decomposition temperature	Not Available	
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	Not Available	
Initial boiling point and boiling range (°C)	110	Molecular weight (g/mol)	Not Available	
Flash point (°C)	15	Taste	Not Available	
Evaporation rate	3.2 BuAC = 1	Explosive properties	Not Available	
Flammability	HIGHLY FLAMMABLE.	Oxidising properties	Not Available	
Upper Explosive Limit (%)	9.7	Surface Tension (dyn/cm or mN/m)	Not Available	
Lower Explosive Limit (%)	1.4	Volatile Component (%vol)	100	

Vapour pressure (kPa)	5.11	Gas group	Not Available
Solubility in water	Immiscible	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	3.19	VOC g/L	859.15

SECTION 10 STABILITY AND REACTIVITY

Reactivity	See section 7
Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

SECTION 11 TOXICOLOGICAL INFORMATION

Information on toxicological effects

Inhaled	There is strong evidence to suggest that this material can cause, if inhaled once, very serious, irreversible damage of organs. The material can cause experiatory irritation in some persons. The body's response to such irritation can cause further lung damage. Inhalation of vapours may cause drowsiness and dizziness. This may be accompanied by sleepiness, reduced alertness, loss of reflexes, lack of co-ordination, and vertigo. The material has NOT been classified by EC Directives or other classification systems as "harmful by inhalation". This is because of the lack of corroborating animal or human evidence. Inhalation of high concentrations of gas/vapour causes lung irritation with coughing and nausea, central nervous depression with headache and dizziness, slowing of reflexes, fatigue and inco-ordination. Central nervous system (CNS) depression may include general discomfort, symptoms of giddiness, headache, dizziness, nausea, anaesthetic effects, slowed reaction time, slurred speech and may progress to unconsciousness. Serious poisonings may result in respiratory depression and may be fatal. On exposure to mixed trimethylbenzenes, some people may become nervous, tensed, anxious and have difficult breathing. There may be a reduction red blood cells and bleeding abnormalities. There may also be drowsiness. Inhalation of naphthalene vapour is linked with headache, loss of appetite, nausea, damage to the eyes and kidneys. According to animal testing, long term exposure may cause excessive weakness and increased salivation, weight loss, difficulty breathing, collapse, and evidence of damage to the skin, liver and lungs. Animal testing showed no toxic effects from inhaling PGMEA except at very high concentrations. A concentration of 1000 parts per million (0.1%) caused no effects. The acute toxicity of inhaled alkylbenzene is best described by central nervous system (cond or numbness, twitching, tremors, convulsions, unconsciousness, depression of breathing, and arrest. Heart stoppage may result
Ingestion	There is strong evidence to suggest that this material can cause, if swallowed once, very serious, irreversible damage of organs. The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence. Ingestion of naphthalene and related compounds may produce abdominal cramps with nausea, vomiting, diarrhoea, headache, profuse sweating, listlessness, confusion, and in severe poisonings, coma with or without convulsions. Irritation of the bladder may also occur, producing urgency, painful urination, and the passage of brown or black urine with or without albumin or casts. Central nervous system (CNS) depression may include general discomfort, symptoms of giddiness, headache, dizziness, nausea, anaesthetic effects, slowed reaction time, slurred speech and may progress to unconsciousness. Serious poisonings may result in respiratory depression and may be fatal.
Skin Contact	There is strong evidence to suggest that this material, on a single contact with skin, can cause very serious, irreversible damage of organs. The material may accentuate any pre-existing dermatitis condition Skin contact is not thought to have harmful health effects (as classified under EC Directives); the material may still produce health damage following entry through wounds, lesions or abrasions. Animal testing showed repeated application of commercial grade PGMEA to skin caused slight redness and very mild exfoliation. In humans exposed to methyl ethyl ketone, skin inflammation has been reported. Animal testing has shown methyl ethyl ketone to have high acute toxicity from skin exposure. Workers sensitised to naphthalene and related compounds show an inflammation of the skin with scaling and reddening. Some individuals show an allergic reaction. Open cuts, abraded or irritated skin should not be exposed to this material Entry into the blood-stream, through, for example, cuts, abrasions or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected. Testing in humans suggests that liquid ethyl benzene is absorbed at a greater rate than aniline, benzene, nitrobenzene, carbon disulfide and styrene. Animal testing showed repeated application of the undiluted product to the abdomen resulted in redness, swelling and superficial tissue death

Legend:

Altex Thinning Solvent #127

	(necrosis). The material did appear to be absorbed through the skin i Skin contact with the material may damage the health of the individua	n sufficient quantity to produce outward signs of toxicity. al; systemic effects may result following absorption.	
Eye	This material can cause eye irritation and damage in some persons. Long term exposure to naphthalene has produced clouding of the lens (cataracts) in workers.		
	The vapour when concentrated has pronounced eye irritation effects occurs seek to reduce exposure with available control measures, or e Undiluted propylene glycol monomethyl ether acetate (PGMEA) caus the cornea in animal testing. Two drops of ethylbenzene into the conjunctival sac produced only sl	and this gives some warning of high vapour concentrations. If eye irritation avacuate area. ses moderate discomfort, slight redness of the conjunctiva and slight injury to ight irritation of the conjunctival membrane, but no injury to the cornea.	
Chronic	There has been concern that this material can cause cancer or mutations, but there is not enough data to make an assessment. Repeated or long-term occupational exposure is likely to produce cumulative health effects involving organs or biochemical systems. Long-term exposure to respiratory irritants may result in airways disease, involving difficulty breathing and related whole-body problems. Ample evidence from experiments exists that there is a suspicion this material directly reduces fertility. Animal testing shows repeated exposure to higher concentrations of propylene glycol monomethyl ether acetate (PGMEA) causes mild liver and kidney damage. The beta-isomer, a minor component, may cause birth defects if PGMEA is inhaled during pregnancy. Otherwise, PGMEA has not been shown to have developmental toxicity. It may damage the foetus but only at levels that are also toxic to the mother. Animal testing shows that methyl ethyl ketone may have slight effects on the nervous system, liver, kidney and respiratory system; there may also be developmental effects and an increase in birth defects. However, there is limited information available on the long-term effects of methyl ethyl ketone in humans, and no information is available on whether it causes developmental or reproductive toxicity or cancer. It is generally considered to have low toxicity, but it is often used in combination with other solvents, and the toxic effects of the mixture may be greater than with either solvent alone. Combinations of n-hexane or methyl n-butyl ketone with methyl ethyl ketone may increase the rate of peripheral neuropathy, a progressive disorder of the nerves of the extremities. Combinations with chloroform also show increase in toxicity. Animal testing indicates that inhalation of naphthalene may increase the incidence of respiratory tumours and may aggravate chronic inflammation. Industrial workers exposed to 14 parts per million ethylbenzene experienced headaches, irritability and rapid fatigue. Some workers expos		
	ΤΟΧΙΟΙΤΥ	IRRITATION	
Altex Thinning Solvent #127	Not Available	Not Available	
	ΤΟΧΙΟΙΤΥ	IRRITATION	
naphtha petroleum, light	Dermal (rabbit) LD50: >1900 mg/kg ^[1]	Eye: no adverse effect observed (not irritating) ^[1]	
aromatic solvent	Inhalation (rat) LC50: >7331.62506 mg/l/8h* ^[2]	Skin: adverse effect observed (irritating) ^[1]	
	Oral (rat) LD50: >4500 mg/kg ^[1]		
	тохісіту	IRRITATION	
	Dermal (rabbit) LD50: ~6400-8000 mg/kg ^[2]	Eye (human): 350 ppm -irritant	
methyl ethyl ketone	Inhalation (rat) LC50: 47 mg/l/8H ^[2]	Eye (rabbit): 80 mg - irritant	
	Oral (rat) LD50: 2054 mg/kg ^[1]	Skin (rabbit): 402 mg/24 hr - mild	
		Skin (rabbit):13.78mg/24 hr open	

Altex Thinning Solvent #127	For propylene glycol ethers (PGEs): Typical propylene glycol ethers include propylene glycol n-butyl ether (PnB); dipropylene glycol n-butyl ether (DPnB); dipropylene glycol methyl ether acetate (DPMA) and tripropylene glycol methyl ether (TPM). Testing of a wide variety of propylene glycol methyl ether (TPM). Testing of a wide variety of propylene glycol ethers has shown that propylene glycol-based ethers are less toxic than some ethers of the ethylene series. The common toxicities associated with the lower molecular weight homologues of the ethylene series, such as adverse effects on the reproductive organs, the developing embryo and foetus, blood or thymus gland, are not seen with the commercial-grade propylene glycol ethers. In the ethylene series, metabolism of the terminal hydroxyl group produces and alkoxyacetic acid. The reproductive and developmental toxicities of the lower molecular weight homologues in the ethylene series are due specifically to the formation of methoxyacetic acid and thoxyacetic acids. Longer chain homologues in the ethylene series are not associated with reproductive toxicity, but can cause haemolysis in sensitive species, also through formation of an alkoxyacetic acid. The predominant alpha isomer of all the PGEs (which is thermodynamically favoured during manufacture of PGEs) is a secondary alcohol incapable of forming an alkoxypropionic acid. In contrast, beta-isomers are able to form the alkoxypropionic acids and these are linked to birth defects (and possibly, haemolytic effects). The alpha isomer comprises more than 95% of the isomeric mixture in the commercial product, and therefore PGEs show relatively little toxicity. One of the main metabolites of the eyes, in animal testing, while the remaining members of this category caused little or no eye irritation. None caused skin sensitization. Animal testing showed that repeat dosing caused few adverse effects. Animal testing also shows that PGEs do not cause skin effects or reproductive toxicity. Commercially available PGEs hav

1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2.* Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

Altex	Thinnir	g Sol	vent	#127
-------	---------	-------	------	------

NAPHTHA PETROLEUM, LIGHT AROMATIC SOLVENT	For C9 aromatics (typically trimethylbenzenes – TMBs) Acute toxicity: Animal testing shows that semi-lethal concentrations and doses vary amongst this group. The semilethal concentrations for inhalation range from 6000 to 10000 mg/cubic metre for C9 aromatic naphtha and 18000-24000 mg/cubic metre for 1,2,4- and 1,3,5-TMB, respectively. Irritation and sensitization: Results from animal testing indicate that C9 aromatic hydrocarbon solvents are mildly to moderately irritating to the skin, minimally irritating to the eye, and have the potential to irritate the airway and cause depression of breathing rate. There is no evidence that it sensitizes skin. Repeated dose toxicity: Animal studies show that chronic inhalation toxicity for C9 aromatic hydrocarbon solvents is slight. Similarly, oral exposure does not appear to pose a high toxicity hazard for pure trimethylbenzene isomers. Mutation-causing ability: No evidence of mutation-causing ability and genetic toxicity was found in animal and laboratory testing. Reproductive and developmental toxicity: No definitive effects on reproduction were seen, although reduction in weight in developing animals may been seen at concentrations that are toxic to the mother. * [Devoe] .		
METHYL ETHYL KETONE	The material may cause skin irritation after prolonged vesicles, scaling and thickening of the skin.	or repeated exposure and may produ	ce on contact skin redness, swelling, the production of
Altex Thinning Solvent #127 & NAPHTHA PETROLEUM, LIGHT AROMATIC SOLVENT & METHYL ETHYL KETONE	Asthma-like symptoms may continue for months or even years after exposure to the material ends. This may be due to a non-allergic condition known as reactive airways dysfunction syndrome (RADS) which can occur after exposure to high levels of highly irritating compound. Main criteria for diagnosing RADS include the absence of previous airways disease in a non-atopic individual, with sudden onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. Other criteria for diagnosis of RADS include a reversible airflow pattern on lung function tests, moderate to severe bronchial hyperreactivity on methacholine challenge testing, and the lack of minimal lymphocytic inflammation, without eosinophilia. RADS (or asthma) following an irritating inhalation is an infrequent disorder with rates related to the concentration of and duration of exposure to the irritating substance. On the other hand, industrial bronchitis is a disorder that occurs as a result of exposure due to high concentrations of irritating substance. On the other hand, is completely reversible after exposure ceases. The disorder is characterized by difficulty breathing, cough and mucus production.		
Altex Thinning Solvent #127 & NAPHTHA PETROLEUM, LIGHT AROMATIC SOLVENT	For trimethylbenzenes: Absorption of 1,2,4-trimethylbenzene occurs after exposure by swallowing, inhalation, or skin contact. In the workplace, inhalation and skin contact are the most important routes of absorption; whole-body toxic effects from skin absorption are unlikely to occur as the skin irritation caused by the chemical generally leads to quick removal. The substance is fat-soluble and may accumulate in fatty tissues. It is also bound to red blood cells in the bloodstream. It is excreted from the body both by exhalation and in the urine. Acute toxicity: Direct contact with liquid 1,2,4-trimethylbenzene is irritating to the skin, and breathing the vapour is irritating to the airway, causing lung inflammation. Breathing high concentrations of the chemical vapour causes headache, fatigue and drowsiness. In humans, liquid 1,2,4- trimethylbenzene is irritating to the skin and inhalation of the vapour causes chemical pneumonitis. Direct skin contact causes dilation of blood vessels, redness and irritation. Nervous system toxicity: 1,2,4-trimethylbenzene depresses the central nervous system. Exposure to solvent mixtures in the workplace containing the chemical causes headache, fatigue, nervousness and drowsiness. Subacute/chronic toxicity: Long-term exposure to solvents containing 1,2,4-trimethylbenzene may cause nervousness, tension and inflammation of the bronchi. Painters that worked for several years with a solvent containing 50% 1,2,4-trimethylbenzene and 30% 1,3,5-trimethylbenzene showed nervousness, tension and anxiety, asthmatic bronchitis, anaemia and changes in blood clotting; blood effects may have been due to trace amounts of benzene. Animal testing showed that inhaling trimethylbenzene may alter blood counts, with reduction in lymphocytes and an increase in neutrophils. Genetic toxicity: Animal testing does not show that the C9 fraction causes mutations or chromosomal aberrations. Developmental / reproductive toxicity. Animal testing showed that the C9 fraction of 1,2,4-trimethyl		
Altex Thinning Solvent #127 & METHYL ETHYL KETONE	Methyl ethyl ketone is considered to have a low order of toxicity; however, methyl ethyl ketone is often used in combination with other solvents and the mixture may have greater toxicity than either solvent alone. Combinations of n-hexane with methyl ethyl ketone, and also methyl n-butyl ketone with methyl ethyl ketone may result in an increased in peripheral neuropathy, a progressive disorder of the nerves of the extremities. Combinations with chloroform also show an increase in toxicity.		
Acute Toxicity	¥	Carcinogenicity	✓
Skin Irritation/Corrosion	¥	Reproductivity	✓
Serious Eye Damage/Irritation	¥	STOT - Single Exposure	✓
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	✓
Mutagenicity	×	Aspiration Hazard	✓
		Legend: X – Data either r	not available or does not fill the criteria for classification le to make classification

SECTION 12 ECOLOGICAL INFORMATION

Toxicity					
Altex Thinning Solvent #127	ENDPOINT	TEST DURATION (HR)	SPECIES	VALUE	SOURCE
	Not Available	Not Available	Not Available	Not Available	Not Available
	ENDPOINT	TEST DURATION (HR)	SPECIES	VALUE	SOURCE
	LC50	96	Fish	4.1mg/L	2
naphtha petroleum, light aromatic solvent	EC50	48	Crustacea	3.2mg/L	2
	EC50	72	Algae or other aquatic plants	>1-mg/L	2
	NOEC	72	Algae or other aquatic plants	=1mg/L	1
	ENDPOINT	TEST DURATION (HR)	SPECIES	VALUE	SOURCE
	LC50	96	Fish	2-993mg/L	2
	EC50	48	Crustacea	5-91mg/L	2
methyl ethyl ketone	EC50	72	Algae or other aquatic plants	1-972mg/L	2
	EC0	96	Fish	1-848mg/L	2
	NOEC	96	Fish	1-170mg/L	2

Legend: Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 3. EPIWIN Suite V3.12 (QSAR) - Aquatic Toxicity Data (Estimated) 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

May cause long-term adverse effects in the aquatic environment.

Do NOT allow product to come in contact with surface waters or to intertidal areas below the mean high water mark. Do not contaminate water when cleaning equipment or disposing of equipment wash-waters.

Wastes resulting from use of the product must be disposed of on site or at approved waste sites.

When spilled this product may act as a typical oil, causing a film, sheen, emulsion or sludge at or beneath the surface of the body of water. The oil film on water surface may physically affect the aquatic organisms, due to the interruption of the

oxygen transfer between the air and the water

Oils of any kind can cause:

In drowning of water-fowl due to lack of buoyancy, loss of insulating capacity of feathers, starvation and vulnerability to predators due to lack of mobility

Iethal effects on fish by coating gill surfaces, preventing respiration

+ asphyxiation of benthic life forms when floating masses become engaged with surface debris and settle on the bottom and

adverse aesthetic effects of fouled shoreline and beaches

In case of accidental releases on the soil, a fine film is formed on the soil, which prevents the plant respiration process and the soil particle saturation. It may cause deep water infestation.

For Propylene Glycol Ethers: log Kow's range from 0.309 for TPM to 1.523 for DPnB. Calculated BCFs range from 1.47 for DPnB to 3.16 for DPMA and TPM, indicating low bioaccumulation. Henry's Law Constants are low for all category members, ranging from 5.7 x 10-9 atm-m3/mole for TPM to 2.7 x10-9 atm-m3/mole for PnB. Environmental Fate: Most are liquids at room temperature and all are water-soluble.

Atmospheric Fate: In air, the half-life due to direct reactions with photochemically generated hydroxyl radicals, range from 2.0 hours for TPM to 4.6 hours for PnB. Aquatic/Terrestrial Fate: Most propylene glycol ethers are likely to partition roughly equally into the soil and water compartments in the environment with small to negligible amounts remaining in other environmental compartments (air, sediment, and aquatic biota). In water, most members of this family are "readily biodegradable" under aerobic conditions. In soil, biodegradation is rapid for PM and PMA.

Ecotoxicity: Propylene glycol ethers are unlikely to persist in the environment. Acute aquatic toxicity testing indicates low toxicity for both ethers and acetates. For 1,2,4 - Trimethylbenzene:

Half-life (hr) air: 0.48-16;

Half-life (hr) H2O surface water: 0.24 -672;

Half-life (hr) H2O ground: 336-1344;

Half-life (hr) soil: 168-672;

Henry's Pa m3 /mol: 385 -627;

Bioaccumulation: not significant. 1,2,4-Trimethylbenzene is a volatile organic compound (VOC) substance.

Atmospheric Fate: 1,2,4-trimethylbenzene can contribute to the formation of photochemical smog in the presence of other VOCs. Degradation of 1,2,4-trimethylbenzene in the atmosphere occurs by reaction with hydroxyl radicals. Reaction also occurs with ozone but very slowly (half life 8820 days).

Aquatic Fate: 1,2,4-Trimethylbenzene volatilizes rapidly from surface waters with volatilization half-life from a model river calculated to be 3.4 hours. Biodegradation of 1,2,4-trimethylbenzene has been noted in both seawater and ground water. Various strains of Pseudomonas can biodegrade 1,2,4-trimethylbenzene.

Terrestrial Fate: 1,2,4-Trimethylbenzene also volatilizes from soils however; moderate adsorption to soils and sediments may occur. Volatilization is the major route of removal of 1,2,4-trimethylbenzene from soils; although, biodegradation may also occur. Due to the high volatility of the chemical it is unlikely to accumulate in soil or surface water to toxic concentrations.

Ecotoxicity: No significant bioaccumulation has been noted. 1,2,4-Trimethylbenzene is moderately toxic to fathead minnow and slightly toxic to dungeness crab. 1,2,4-Trimethylbenzene has moderate acute toxicity to aquatic organisms. No stress was observed in rainbow trout, sea lamprey and Daphnia magna water fleas. The high concentrations required to induce toxicity in laboratory animals are not likely to be reached in the environment.

For Aromatic Substances Series:

Environmental Fate: Large, molecularly complex polycyclic aromatic hydrocarbons, or PAHs, are persistent in the environment longer than smaller PAHs. Atmospheric Fate: PAHs are 'semi-volatile substances' which can move between the atmosphere and the Earth's surface in repeated, temperature-driven cycles of deposition and volatilization. Terrestrial Fate: BTEX compounds have the potential to move through soil and contaminate ground water, and their vapors are highly flammable and explosive. Ecotoxicity - Within an aromatic series, acute toxicity increases with increasing alkyl substitution on the aromatic nucleus. The order of most toxic to least in a study using grass shrimp and brown shrimp was dimethylnaphthalenes > methylnaphthalenes >naphthalenes. Anthrcene is a phototoxic PAH. UV light greatly increases the toxicity of anthracene to bluegill sunfish. Biological resources in strong sunlight are at more risk than those that are not. PAHs in general are more frequently associated with chronic risks. For C9 aromatics (typically trimethylbenzene - TMBs)

Chemicals in this category possess properties indicating a hazard for the environment (acute toxicity for fish, invertebrates, and algae from 1 to 10 mg/L). Category members are readily biodegradable, except 1,3,5-trimethylbenzene (CAS RN 108-67-8). Category members are not expected to be bioaccumulative.

Environmental Fate:

In the air, category member constituents have the potential to rapidly degrade through indirect photolytic processes mediated primarily by hydroxyl radicals with calculated degradation half-lives ranging from 0.54 to 2.81 days (based on a 12-hour day and a hydroxyl radical concentration of 5x10+5). Aqueous photolysis and hydrolysis will not contribute to the transformation of category chemical constituents in aquatic environments because they are either poorly reactive or not susceptible to these reactions.

Results of the Mackay Level I environmental distribution model show that chemical constituents of C9 Aromatic Hydrocarbon Solvents Category members have the potential to partition to air (96.8 to 98.9 %), with a negligible amount partitioning to water (0.2 to 0.6%) and soil (0.9 to 2.7%). In comparison, Level III modeling indicates that category members partition primarily to soil (66.3 to 79.6%) and water (17.8 to 25.0%) compartments rather than air (2.4 to 8.4%) when an equal emission rate (1000 kg/hr) is assumed to each of the air, water, and soil compartments. When release (1000 kg/hr) is modeled only to either the air, water, or soil compartment, constituents are indicated in the modeling to partition primarily (>94%) to the compartment to which they are emitted as advection and degradation influence constituent concentration in compartments to which constituents are not released. Solvent naphtha, (pet.), light aromatic (CAS RN 64742-95-6), 1,2,4-trimethylbenzene (CAS RN 95-63-6), and 1-ethyl-3-methylbenzene (CAS RN 620-14-4) were determined to be readily biodegradable based on the studies that used the TG OECD 301F (the latter substance is used to characterize the potential biodegradability of the category member, ethylmethylbenzene (CAS RN 25550-14-5)). These three substances exceed 60%

biodegradation in 28 days and met the 10-day window criterion for ready biodegradation. In comparison 1,3,5-trimethylbenzene (CAS RN 108-67-8) was not readily biodegradable. It achieved 42% biodegradation after 28 days and 60% biodegradation after 39 days. The result for the multi-constituent substance (CAS RN 64742-95-6), a UVCB, characterizes the biodegradability of that substance as a whole, but it does not suggest that each constituent is equally biodegradable. As with all ready biodegradation test guidelines, the test system and study design used with these substances (OECD TG 301F) is not capable of distinguishing the relative contribution of the substances' constituents to the total biodegradation measured.

Based on Henry's Law constants (HLCs) representing a potential to volatilize from water that range from 590 to 1000 Pa-m3/mole, the potential to volatilize from surface waters for chemicals in the C9 Aromatic Hydrocarbon Solvents Category is expected to be high.

Based on the measured bioconcentration factors that range from 23 to 342 for 1,2,4-trimethylbenzene and 1,3,5-trimethylbenzene, the category members are not expected to be bioaccumulative.

Ecotoxicity

Acute toxicity values used to characterize this category for fish (LL50; LC50) and invertebrates (EL50; EC50) range from 3.5 to 9.2 mg/L, based on measured data. For algae, one study for a category member (CAS RN 64742-95-6) resulted in a 72-hr EC50 of 2.4 mg/L (biomass) and 2.7 mg/L (growth rate) based on measured concentrations. The algal 72-hour NOEC (no observed effect concentration) for biomass and growth rate is 1.3 mg/L, based on mean measured concentrations. A 21-day Daphnia magna reproduction study with 1,3,5-trimethylbenzene (CAS RN 108-67-8) resulted in a NOEC value of 0.4 mg/L, based on a minimum measured value. For Methyl Ethyl Ketone:

log Kow: 0.26-0.69; log Koc: 0.69; Koc: 34; Half-life (hr) air: 2.3; Half-life (hr) H2O surface water: 72-288; Henry's atm m3 /mol: 1.05E-05; BOD 5: 1.5-2.24, 46%;

COD: 2.2-2.31, 100%; ThOD: 2.44; BCF: 1.

Environmental Fate: Terrestrial Fate - Measured Koc values of 29 and 34 were obtained for methyl ethyl ketone is silt loams. Methyl ethyl ketone is expected to have very high mobility in soil. Volatilization of methyl ethyl ketone from moist and dry soil surfaces is expected. The volatilization half-life of methyl ethyl ketone from silt and sandy loams was measured as 4.9 days. Methyl ethyl ketone is expected to biodegrade under both aerobic and anaerobic conditions.

Aquatic Fate: Methyl ethyl ethyl ketone is not expected to adsorb to suspended solids and sediment in water and is expected to volatilize from water surfaces. Estimated half-lives for a model river and model lake are 19 and 197, hours respectively. Bioconcentration is expected to be low in aquatic systems.

Atmospheric Fate: Methyl ethyl ketone will exist solely as a vapour in the ambient atmosphere. Vapour-phase methyl ethyl ketone is degraded in the atmosphere by reaction with photochemically-produced hydroxyl radicals; the half-life for this reaction in air is estimated to be about 14 days. Methyl ethyl ketone is also expected to undergo photodecomposition in the atmosphere by natural sunlight.

Ecotoxicity: Methyl ethyl ketone is not acutely toxic to fish, specifically, bluegill sunfish, guppy, goldfish, fathead minnow, mosquito fish, Daphnia magna water fleas and brine shrimp. For Xylenes:

log Koc : 2.05-3.08; Koc : 25.4-204; Half-life (hr) air : 0.24-42; Half-life (hr) H2O surface water : 24-672; Half-life (hr) H2O ground : 336-8640; Half-life (hr) soil : 52-672; Henry's Pa m3 /mol : 637-879; Henry's atm m3 /mol - 7.68E-03; BOD 5 if unstated - 1.4,1%; COD - 2.56,13% ThOD - 3.125 : BCF : 23; log BCF : 1.17-2.41.

Environmental Fate: Most xylenes released to the environment will occur in the atmosphere and volatilisation is the dominant environmental fate process. Soil - Xylenes are expected to have moderate mobility in soil evaporating rapidly from soil surfaces. The extent of the degradation is expected to depend on its concentration, residence time in the soil, the nature of the soil, and whether resident microbial populations have been acclimated. Xylene can remain below the soil surface for several days and may travel through the soil profile and enter groundwater. Soil and water microbes may transform it into other, less harmful compounds, although this happens slowly. It is not clear how long xylene remains trapped deep underground in soil or groundwater, but it may be months or years.

Atmospheric Fate: Xylene evaporates quickly into the air from surface soil and water and can remain in the air for several days until it is broken down by sunlight into other less harmful chemicals. In the ambient atmosphere, xylenes are expected to exist solely in the vapour phase. Xylenes are degraded in the atmosphere with an estimated atmospheric lifetime of about 0.5 to 2 days. Xylene may contribute to photochemical smog formation. p-Xylene has a moderately high photochemical reactivity under smog conditions, higher than the other xylene isomers. The photooxidation of p-xylene results in the production of carbon monoxide, formaldehyde, glyoxal, methylglyoxal, 3-methylghenzylnitrate, m-tolualdehyde, 4-nitro-3-xylene, 5-nitro-3-xylene, 2,6-dimethylphenol.

Aquatic Fate: p-xylene may adsorb to suspended solids and sediment in water and is expected to volatilise from water surfaces. Estimated volatilisation half-lives for a model river and model lake are 3 hours and 4 days, respectively. Measurements taken from goldfish, eels and clams indicate that bioconcentration in aquatic organisms is low. Photo-oxidation in the presence of humic acids may play an important role in the abiotic degradation of p-xylene. p-Xylene is biodegradable and has been observed to degrade in pond water however; it is unclear if it degrades in surface waters. p-Xylene has been observed to degrade in anaerobic and aerobic groundwater; however, it is known to persist for many years in groundwater, at least at sites where the concentration might have been quite high. Ecotoxicity: Xylenes are slightly toxic to fathead minnow, rainbow trout and bluegill and not acutely toxic to water fleas. For Photobacterium phosphoreum EC50 (24 h): 0.0084 mg/L. and Gammarus lacustris LC50 (48 h): 0.6 mg/L.

Environmental Fate: Several glycol ethers have been shown to biodegrade however; biodegradation slows as molecular weight increases. No glycol ethers that have been tested demonstrate marked resistance to biodegradative processes. Atmospheric Fate: Upon release to the atmosphere by evaporation, high boiling glycol ethers are estimated to undergo photo-degradation (atmospheric half lives = 2.4-2.5 hr). Aquatic Fate: In water, glycol ethers undergo biodegradative to typically 47-92% after 8-21 days) and have a low potential for bioaccumulation (log Kow ranges from -1.73 to +0.51). Ecotoxicity: Tri- and tetra ethylene glycol ethers are "practically non-toxic" to aquatic species. No major differences are observed in the order of toxicity going from the methyl- to the butyl ethers. Glycols exert a high oxygen demand for decomposition and once released to the environment death of aquatic organisms occurs if dissolved oxygen is depleted. For Ketones: Ketones, unless they are alpha, beta--unsaturated ketones, can be considered as narcosis or baseline toxicity compounds.

Aquatic Fate: Hydrolysis of ketones in water is thermodynamically favourable only for low molecular weight ketones. Reactions with water are reversible with no permanent change in the structure of the ketone substrate. Ketones are stable to water under ambient environmental conditions. When pH levels are greater than 10, condensation reactions can occur which produce higher molecular weight products. Under ambient conditions of temperature, pH, and low concentration, these condensation reactions are unfavourable. Based on its reactions in air, it seems likely that ketones undergo photolysis in water.

Terrestrial Fate: It is probable that ketones will be biodegraded by micro-organisms in soil and water.

Ecotoxicity: Ketones are unlikely to bioconcentrate or biomagnify.

For naphthalene:

Environmental Fate: Naphthalene may be reach surface water and soil through transportation in water or being carried by air. Most airborne naphthalene is in a vapour form and hence deposition is expected to be slow. A minimal amount of naphthalene emitted to the air is transported to other environmental components mostly by dry deposition. Naphthalene in surface water may volatililize into the atmosphere, depending on environmental condiditons. It remains in solution in water, with only small amounts associated with suspended material and benthic sediments. While naphthalene is readily volatilized from aerated soils, it adheres to soils with a high organic content. Adsorption to aquifer material reduces transportation of naphthalene through groundwater, and the presence of nonionic organic compounds such as tetrachloroethene may enhance sorption to materials that contain low carbon content. Bioconcentration of naphthalene is moderate in aquatic organisms. It is readily metabolized by fish, and invertebrates that are placed in pollutant free water rapidly eliminate any traces of the pollutant. While bioaccumulation in the food chain is unlikely, exposure of cows and chickens to naphthalene could lead to naphthalene being present in milk and eggs. While the data on the transport and partitioning of methylnaphthalenes in the environment is limited, the characteristics of these chemicals are similar to naphthalene, so they are expected to behave in a similar manner to naphthalene in the environment, and produce the same effects on aquatic organisms. Biodegradation of naphthalene occurs relatively quickly in aquatic systems. Methylnaphthalenes are biodegraded under aerobic conditions after adaptation. Degradation rates are highest in water constantly polluted with petroleum. Naphthalene biodegradation rates are higher in sediment than in the water column above it. Methylnaphthalenes biodegrades more slowly. Reported half-lives in sediments were 46 weeks for 1-methylnaphthalene and ranged from 14 to 50 weeks for 2-methylnaphthalene. In soils, the potential for biodegradation is an important factor for biological remediation of soil. Studies on biodegradation of PAHs suggest that adsorption to the organic matter significantly reduces the bioavailability for microorganisms, and thus the biodegradability, of PAHs, including naphthalene. Biodegradation is accomplished through the action of aerobic microorganisms and is reduced in anaerobic soil conditions. Naphthalene biodegrades to carbon dioxide in aerobic soils, with salicylate as an intermediate product. Abiotic degradation of naphthalene seldom occurs in soils. As with naphthalene, 1-Methylnaphthalene is easily volatilised from aerated soil, and the biodegradation half-life averages between 1.7 and 2.2 days

Ecotoxicity: Acute toxicity data on naphthalene for several fish species (freshwater and marine), show 96h LC50 values range from 1.8 to 7.8 mg/L. Comparable results were obtained with other vertebrates (amphibians). From chronic toxicity tests, a precise NOEL is not clearly determined. A NOEC of 0.12 mg/L was observed in a 40 days test on juvenile pink salmon, but 50% mortality at 0.11 mg/L was calculated for trout fry exposed during hatching.Several data are also available for invertebrates, showing 48h EC50 values ranging from 2.1 to 24 mg/L. While chronic data on freshwater invertebrates and algae are questionable, a 50% photosynthesis reduction was observed at 2.8 mg/L in 4 hours experiments.QSAR prediction models give results consistent with experimental short-term data on fish daphnia and algae.

For Ethylbenzene: Log Kow: 3.15; Log Koc: 1.98-3.04; Koc: 164; Log Kom: 1.73-3.23; Vapor Pressure: 1270 Pa (1.27 kPa); Half-life (hr) air: 0.24-85.6; Half-life (hr) Surface Water: 5-240; Half-life (hr) Soil: 72-240; Henry's Pa m3 /mol: 748-887; Henry's atm m3 /mol: 8.44; Water Solubility: 169 mg/l @ 25 C.

Atmospheric Fate: Ethylbenzene partitions primarily to the air from water and soil, where it is broken down. Ethylbenzene is volatile and will rapidly evaporate. Light breakdown is the primary route of removal in the environment, with an estimated half-life of 1 day.

Terrestrial Fate: This substance is inherently biodegradable in the soil, in the presence of oxygen and not rapidly biodegradable in low oxygen conditions. Ethylbenzene is expected to be moderately adsorbed to soil.

Aquatic Fate: Ethylbenzene is considered inherently biodegradable and removal from water occurs primarily by evaporation but, in the summer, biological breakdown plays a key role in the removal process. This substance is removed biologically in oxygenated waters and removal is slow in low oxygen waters.

Ecotoxicity: Ethylbenzene is not expected to bioaccumulate. The substance ranges from slightly to moderately toxic to aquatic organisms. The substance is slightly toxic to fathead minnow, rainbow trout, and Atlantic silverside. Ethylbenzene is slightly toxic to Daphnia magna and Ceriodaphia dubia water fleas and can inhibit growth in green algae and Skeletonema costatum diatoms.

DO NOT discharge into sewer or waterways

Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
methyl ethyl ketone	LOW (Half-life = 14 days)	LOW (Half-life = 26.75 days)

Bioaccumulative potential

Ingredient	Bioaccumulation
methyl ethyl ketone	LOW (LogKOW = 0.29)
Mobility in soil	
Ingredient	Mobility

SECTION 13 DISPOSAL CONSIDERATIONS

Waste treatment methods

Product / Packaging disposal	 Containers may still present a chemical hazard/ danger when empty. Return to supplier for reuse/ recycling if possible. Otherwise: If container can not be cleaned sufficiently well to ensure that residuals do not remain or if the container cannot be used to store the same product, then puncture containers, to prevent re-use, and bury at an authorised landfill. Where possible retain label warnings and SDS and observe all notices pertaining to the product. Legislation addressing waste disposal requirements may differ by country, state and/ or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked. A Hierarchy of Controls seems to be common - the user should investigate: Reduction Reuse Recycling Disposal (fall else fails) This material may be possible to reclaim the product by filtration, distillation or some other means. Shelf life considerations should also be applied in making decisions of this type. Note that properties of a material may change in use, and recycling or reuse may not always be appropriate. DO NOT allow wash water from cleaning or process equipment to enter drains. It may be necessary to collect all wash water for treatment before disposal. In all cases disposal to sever may be subject to local laws and regulations and these should be considered first. Where in doubt contact the responsible authority. Recycle wherever possible. Consult manufacturer for recycling options or consult local or regional waste management authority for disposal if no suitable treatment or disposal facility can be identified. Dispose of by: burial in a land-fill specifically licensed to accept chemical and / or pharmaceutical wastes or Incineration in a licensed apparatus (after admixture with suitable combustible material).
	Decontaminate empty containers. Observe all label safeguards until containers are cleaned and destroyed.

SECTION 14 TRANSPORT INFORMATION

Labels Required



Land transport (ADG)

UN number	1263
UN proper shipping name	PAINT (including paint, lacquer, enamel, stain, shellac, varnish, polish, liquid filler and liquid lacquer base) or PAINT RELATED MATERIAL (including paint thinning or reducing compound)
Transport hazard class(es)	Class 3 Subrisk Not Applicable
Packing group	II
Environmental hazard	Not Applicable
Special precautions for user	Special provisions 163 367 Limited quantity 5 L

Air transport (ICAO-IATA / DGR)

UN number	1263	
UN proper shipping name	Paint (including paint, lacquer, enamel, stain, shellac, varnish, polish, liquid filler and liquid lacquer base); Paint related material (including paint thinning or reducing compounds)	
Transport hazard class(es)	ICAO/IATA Class 3 ICAO / IATA Subrisk Not Applicable ERG Code 3L	

Packing group	Ш			
Environmental hazard	Not Applicable			
Special precautions for user	Special provisions	A3 A72 A192		
	Cargo Only Packing Instructions	364		
	Cargo Only Maximum Qty / Pack	60 L		
	Passenger and Cargo Packing Instructions	353		
	Passenger and Cargo Maximum Qty / Pack	5 L		
	Passenger and Cargo Limited Quantity Packing Instructions	Y341		
	Passenger and Cargo Limited Maximum Qty / Pack	1L		

Sea transport (IMDG-Code / GGVSee)

UN number	1263	
UN proper shipping name	PAINT (including paint, lacquer, enamel, stain, shellac, varnish, polish, liquid filler and liquid lacquer base) or PAINT RELATED MATERIAL (including paint thinning or reducing compound)	
Transport hazard class(es)	IMDG Class 3 IMDG Subrisk Not Applicable	
Packing group	ll	
Environmental hazard	Not Applicable	
Special precautions for user	EMS NumberF-E , S-ESpecial provisions163 367Limited Quantities5 L	

Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

SECTION 15 REGULATORY INFORMATION

Safety, health and environmental regulations / legislation specific for the substance or mixture

NAPHTHA PETROLEUM, LIGHT AROMATIC SOLVENT IS FOUND ON THE FOLLOWING REGULATORY LISTS

Australia Dangerous Goods Code (ADG Code) - Dangerous Goods List Australia Dangerous Goods Code (ADG Code) - List of Emergency Action Codes

Australia Hazardous Chemical Information System (HCIS) - Hazardous Chemicals Australia Inventory of Chemical Substances (AICS) Australia Standard for the Uniform Scheduling of Medicines and Poisons (SUSMP) -

Schedule 5

Chemical Footprint Project - Chemicals of High Concern List

GESAMP/EHS Composite List - GESAMP Hazard Profiles

METHYL ETHYL KETONE IS FOUND ON THE FOLLOWING REGULATORY LISTS

Australia Dangerous Goods Code (ADG Code) - Dangerous Goods List

Australia Dangerous Goods Code (ADG Code) - List of Emergency Action Codes

Australia Exposure Standards

Australia Hazardous Chemical Information System (HCIS) - Hazardous Chemicals Australia Inventory of Chemical Substances (AICS)

Australia Standard for the Uniform Scheduling of Medicines and Poisons (SUSMP) - Schedule 5 $\,$

National Inventory Status

IMO IBC Code Chapter 17: Summary of minimum requirements IMO MARPOL (Annex II) - List of Noxious Liquid Substances Carried in Bulk IMO Provisional Categorization of Liquid Substances - List 2: Pollutant only mixtures containing at least 99% by weight of components already assessed by IMO International Air Transport Association (IATA) Dangerous Goods Regulations International Maritime Dangerous Goods Requirements (IMDG Code) United Nations Recommendations on the Transport of Dangerous Goods Model Regulations

GESAMP/EHS Composite List - GESAMP Hazard Profiles IMO IBC Code Chapter 17: Summary of minimum requirements IMO MARPOL (Annex II) - List of Noxious Liquid Substances Carried in Bulk International Air Transport Association (IATA) Dangerous Goods Regulations International Maritime Dangerous Goods Requirements (IMDG Code) United Nations Recommendations on the Transport of Dangerous Goods Model Regulations

Australia - AICSYesCanada - DSLYesCanada - NDSLNo (propylene glycol monomethyl ether acetate; naphtha petroleum, light aromatic solvent; xylene; methyl ethyl ketone)China - IECSCYesEurope - EINEC / ELINCS / NLPYesJapan - ENCSYesKorea - KECIYesNew Zealand - NZIoCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesYesYes	National Inventory	Status
Canada - DSLYesCanada - NDSLNo (propylene glycol monomethyl ether acetate; naphtha petroleum, light aromatic solvent; xylene; methyl ethyl ketone)China - IECSCYesEurope - EINEC / ELINCS / NLPYesJapan - ENCSYesKorea - KECIYesNew Zealand - NZIOCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesYesYes	Australia - AICS	Yes
Canada - NDSLNo (propylene glycol monomethyl ether acetate; naphtha petroleum, light aromatic solvent; xylene; methyl ethyl ketone)China - IECSCYesEurope - EINEC / ELINCS / NLPYesJapan - ENCSYesKorea - KECIYesNew Zealand - NZIoCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesVietnam - NCIYes	Canada - DSL	Yes
China - IECSCYesEurope - EINEC / ELINCS / NLPYesJapan - ENCSYesKorea - KECIYesNew Zealand - NZIOCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesVietnam - NCIYes	Canada - NDSL	No (propylene glycol monomethyl ether acetate; naphtha petroleum, light aromatic solvent; xylene; methyl ethyl ketone)
Europe - EINEC / ELINCS / NLPYesJapan - ENCSYesKorea - KECIYesNew Zealand - NZIOCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesYietnam - NCIYes	China - IECSC	Yes
Japan - ENCSYesKorea - KECIYesNew Zealand - NZIoCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesVietnam - NCIYes	Europe - EINEC / ELINCS / NLP	Yes
Korea - KECIYesNew Zealand - NZIoCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesVietnam - NCIYes	Japan - ENCS	Yes
New Zealand - NZIoCYesPhilippines - PICCSYesUSA - TSCAYesTaiwan - TCSIYesMexico - INSQYesVietnam - NCIYes	Korea - KECI	Yes
Philippines - PICCS Yes USA - TSCA Yes Taiwan - TCSI Yes Mexico - INSQ Yes Vietnam - NCI Yes	New Zealand - NZIoC	Yes
USA - TSCA Yes Taiwan - TCSI Yes Mexico - INSQ Yes Vietnam - NCI Yes	Philippines - PICCS	Yes
Taiwan - TCSI Yes Mexico - INSQ Yes Vietnam - NCI Yes	USA - TSCA	Yes
Mexico - INSQ Yes Vietnam - NCI Yes	Taiwan - TCSI	Yes
Vietnam - NCI Yes	Mexico - INSQ	Yes
	Vietnam - NCI	Yes

Issue Date: 25/02/2020 Print Date: 26/02/2020

Altex Thinning Solvent #127

Russia - ARIPS	Yes
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory and are not exempt from listing(see specific ingredients in brackets)

SECTION 16 OTHER INFORMATION

Revision Date	25/02/2020
Initial Date	07/12/2017
SDS Version Summary	

Version	Issue Date	Sections Updated
1.3.1.1.1	25/02/2020	Acute Health (eye), Acute Health (inhaled), Acute Health (skin), Acute Health (swallowed), Advice to Doctor, Chronic Health, Classification, Environmental, Exposure Standard, First Aid (inhaled), First Aid (skin), First Aid (swallowed), Handling Procedure, Ingredients, Physical Properties, Storage (storage incompatibility), Supplier Information, Use, Name

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

Definitions and abbreviations

PC-TWA: Permissible Concentration-Time Weighted Average PC-STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit。 IDLH: Immediately Dangerous to Life or Health Concentrations OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value LOD: Limit Of Detection OTV: Odour Threshold Value BCF: BioConcentration Factors BEI: Biological Exposure Index Powered by AuthorITe, from Chemwatch.