

FEATURES

- Excellent gloss retention
- Excellent aged recoatability when cleaned with Altex P40 Cleaner
- Hard, tough coating resists damage
- Good chemical and solvent resistance
- Designed for airless and air spray
- Proven performance in marine environments

RECOMMENDED USES

Elite 239 is a high performance, high gloss, acrylic polyurethane which will provide excellent gloss and colour retention as well as resistance to moderate/severe marine environments.

Elite 239 is recommended for use on:

- Superstructures and Cabin Tops
- Topsides
- Bulwarks and Gunwales
- Handrails
- Galley and Saloon areas
- Decks (may be used with Altex Non-Skid Particles fine grade where added slip resistance is desired)

Elite 239 may be mixed with Altex Flattening Paste to reduce glare off cabin tops, decks etc. Refer to Altex Flattening Paste Data Sheet for further information.

SPECIFICATION DATA

Generic Type:	Aliphatic Acrylic Polyurethane
Colour:	White, AY&B Standard and Custom Colours (refer to colour card)
Packaging:	5 litre kits
Mix Ratio:	4:1 by volume
Gloss:	High Gloss
VOC:	400 g/L (mixed)
Thinner:	Spray: Altex Thinning Solvent #20 Touch-Up: Altex Thinning Solvent #22
Pot-Life:	4 hours at 25°C
Induction Time:	15 minutes at 25°C
Storage:	Store under cool, dry conditions
Shelf Life:	Part A: 24 months at 25°C Part B: 12 months at 25°C

When kept at recommended storage conditions and in original unopened containers. For products/components exceeding the stated shelf life, contact Technical Services for further advice.

Temp Resistance:	up to 121°C			
Volume Solids:	54% ±2%			
Theoretical Coverage Rate:	10.8 sq. metres per litre at 50 microns dry 7.2 sq. metres per litre at 75 microns dry			
Recommended Film Thickness Per Coat:	92-138 microns wet to obtain 50-75 microns dry			
Application:	Spray (brush / roller application for touch up only)			
Dry Times (50µm DFT / 50% RH):				
Min. Recoat:	5°C	15°C	25°C	30°C
	24 hours	12 hours	4 hours	4 hours
Max Recoat:	Extended – Refer to AY&B Technical Services for further advice			
Dry To Handle:	5°C	15°C	25°C	30°C
	30 hours	16 hours	6 hours	5 hours
Application Conditions:				
Condition	Material	Surface	Ambient	Humidity
Minimum	12°C	12°C	12°C	0%
Maximum	32°C	35°C	35°C	80%
Optimum	16-24°C	16-24°C	16-24°C	30-70%
This product requires the substrate temperature to be above the dew point				

SURFACE PREPARATION

All surfaces should be clean, dry, and free from all contaminants.

All undercoated & sanded surfaces must be thoroughly dedusted before application of the Elite finish coat. We also strongly recommend the use of **Altex C50 Surface Cleaner** to aid removal of sanding particles, and light grease/oil contamination. This is often employed prior to tack ragging.

Use **Elite 239** over sanded **AY&B Epoxy Barrier Undercoat** or **AY&B Polyurethane Undercoat**. May also be used directly over suitably prepared sound and compatible existing paint systems.

DIRECTIONS FOR USE

Mixing:

Elite 239 is a two-component product supplied in kits which contain the correct (4:1 v/v) ratio of ingredients.

The entire contents of each container must be mixed.

Power mix Part A first to obtain a smooth, homogeneous condition. After mixing Part A, add Part B slowly with continued agitation. Allow an induction time of 30 minutes before application.

The pot life of the mixed material at 25°C is 4 hours. Higher temperatures will reduce the working life of the coating; lower temperatures will increase it.

Thinning:

Thinning maybe required to assist application. Any solvent addition should be made after the two components are thoroughly mixed. Use Altex Thinner #20 or #25 (slow evaporating) only.

Excessive thinning can cause low film thickness and coating defects.

Application:

Application by either conventional spray or airless spray equipment is the preferred method. **Elite 239** can be applied by brush and roller for touch-up and repair to small areas,

Suggested spray equipment:

Conventional Air Spray:

1.2mm to 1.6mm Fluid tip with appropriate air cap

Airless Spray:

Pump Ratio 30:1

Material Hose 3/8" I.D min

Tip Size 0.015 – 0.019

(Note: The above is a guide. Other equipment to the above may be used.)

Additional coats maybe required to achieve the desired opacity and depth of colour, depending on the colour selected.

Clean Up: Use Altex Thinning Solvent #20 or #25

PRECAUTIONS

For DIY & Professional Use: Read and follow all the caution statements on this Product Data Sheet, the product label, and the Safety Data Sheet (SDS) for health and safety information prior to use.

Elite 239 is flammable. Keep away from heat, sparks, and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

Elite 239 contains isocyanate. When sprayed it may be harmful by inhalation - do not breath vapour of spray. Wear suitable clothing, gloves, eye, and face protection, including suitable breathing protection such as an air supplied respirator or hood.

Additional information is available from the SafeWork Australia and Worksafe New Zealand Approved Code of Practice for the safe use of Isocyanates. We recommend that the latest information be obtained and read carefully. This information is being constantly updated and needs to be clearly understood by applicators prior to the use of this type of coating.

WWW.ALTEXBOATPAINT.COM

**Head Office New Zealand
Altex Coatings Ltd**
91-111 Oropi Road
Greerton, Tauranga 3112
Ph : +64 7 541 1221
Fax : +64 7 541 1310

**Head Office Australia
Resene Paints (Aust) Ltd
Industrial & Marine Division**
7 Production Avenue, Molendinar
Queensland 4214
Ph : +61 7 5512 6600
Fax : +61 7 5512 6697

DISCLAIMER

The information in this datasheet is provided as a guide only and is provided without warranty, implied or otherwise. It is your responsibility to determine the suitability of any information or product for the use contemplated. Conditions of use, application and the substrate are beyond our control so no liability whatsoever (whether as to coverage, performance, injury or otherwise) is accepted for the information contained herein. Data sheets may change from time to time and it is your responsibility to ensure you have the latest product datasheet and material safety data sheet from your supplier. Check the data sheet date with the listings at www.altexcoatings.com Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.